


TUSIL® PURE PREMIUM



SMOOTH, GLOSSY, WHITE,
HEAT RESISTANT SILICONE
STAINLESS STEEL WIRE HELIX
HIGH TEMPERATURE
RESISTANT TEXTILES
TRANSLUCENT SILICONE

Suction and delivery hose suitable for cosmetic, pharmaceutical and food products. Hose tested according to the main norms for food contact materials (FCM – Reg. (CE) 1935/2004). Manufactured according to GMP (Reg. (CE) 2023/2006). Not intended for use as an implant material. Not suitable for blood or human fluids.

DESCRIPTION

Tube

silicone, translucent, phthalates free, tested in compliance with 1907/2006/CE (REACH). Meets FDA 21 CFR 177.2600; USP class VI main requirements; European Pharmacopoeia ed. 8.1/2014 3.1.9; ISO 10993 - 5:2009, 11:2009; BfR XV; REGULATION 1935/2004/CE; DM 21/03/1973 and subsequent amendments; Japan Ministry of Health and Welfare Notice No.370,1959, No.201,2006 and revision 2012; 3-A RPSCQC for (62-02) Hose Assemblies.

Reinforcement

high temperature resistant textiles, stainless steel wire helix

Cover

smooth, platinum-cured silicone, white, glossy cover. Heat, ageing and ozone resistant

Marking

TUDERTECHNICA TUSIL® PURE PREMIUM

TECHNICAL CHARACTERISTICS

Temperature range : -60°C / +200°C (-76°F / +392°F)

The operating temperature of the hose is directly dependent upon the specific fluid been conveyed and the length of time the fluid is in contact with the hose.

Norm : ISO 1307 for dimensional tolerances



refer to guidelines for cleaning and sanitizing on Tudertechnica website



Inside diameter		Outside diameter		Vacuum		Working pressure		Burst pressure		Appr. weight		Bending radius	
[mm]	[in]	[mm]	[in]	[bar]	[psi]	[bar]	[psi]	[bar]	[psi]	[kg/mt]	[lbs/ft]	[mm]	[in]
13	0,50	23	0,91	0,9	13	15	225	45	675	0,38	0,25	60	2,36
16	0,63	26	1,02	0,9	13	14	210	42	630	0,44	0,29	70	2,76
19	0,75	29	1,14	0,9	13	13	195	39	585	0,50	0,34	80	3,15
25	1,00	35	1,38	0,9	13	10	150	30	450	0,61	0,41	100	3,94
32	1,25	42	1,65	0,9	13	8	120	24	360	0,76	0,51	130	5,12
38	1,50	49	1,93	0,9	13	7	105	21	315	1,05	0,70	155	6,10
51	2,00	62	2,44	0,9	13	6	90	18	270	1,36	0,91	210	8,27

Data refer to ambient temperature (20°C); we recommend a reduction of 20% working pressure for every 100°C of temperature increase.

Also available as CRUSH RESISTANT with thermoplastic helix and D without the reinforcing helix. We reserve the right to supply in random lengths shorter than 40mt.

REV-2022-02-18